# **Technical Data Sheet TON 200**



# **Chemical Composition**

Nickel	Silicon	Chromium	Copper
2.4 %	0.6 %	0.5 %	Rem.

Note: Cu + Sum of Named Elements, 99.5% min.

### **Matters Needing Attention**

Due to the very high thermal conductivity, EDM'ing times will extend and a higher electrode wear will result. Using of high speed milling is recommended to mill as close as possible to finished shape so that EDM'ing removal of material will be less.

## **Mechanical and Physical Properties**

Properties (1)	Metric	US Customary
Brinell Hardness	200 HB	200 HB
Tensile Strength	655 MPa	95 ksi
Yield Strength <sup>(2)</sup>	520 MPa	75 ksi
Elongation	12 %	12 %
Density	8.71 g/cm <sup>3</sup>	0.315 lb/in <sup>3</sup>
Electrical Conductivity	48 %IACS	27.8 Ms/m
Thermal Conductivity	212 W/m·K	122 Btu/hr·ft·°F
Coefficient of <sup>(3)</sup> Thermal Expansion	17.5x10 <sup>-6</sup> /°C	9.7x10 <sup>-6</sup> /°F

- (1) Typical values measured at room temperature, 20°C (68°F), unless otherwise stated.
- (2) Offset yield strength set at 0.2% strain.
- (3) Typical value measured at 20-300°C (68-572°F).

# **Material properties**

Beryllium-Free, High Hardness, High Strength, Heat Resistance, Excellent Electrical Conductivity, Excellent Thermal conductivity.

### **Typical Uses**

Injection Mold: Ejector Pins, Cores,
Cavities, Inserts, Ingate Sleeves
Hot Runner: Hot Runner Nozzles
Blow Mold: Cavities, Inserts,
Pinch-offs, Blow Pins
Low Pressure Casting Molds
Die Casting: Plunger Tips
Resistance Welding: Resistance
Welding Tips, Wheels and Fixtures
Stud Welding: Collets and Tips
Other: Current Carrying Arms,
Current Carrying Shafts

### **Fabrication Properties**

Machinability Rating: 30% (Free-Cutting Brass, C36000 is defined as 100%). Cemented carbide cutting tool is suggested for various machining. Good lubricating and cooling should be guaranteed.

Forgeability Rating: 50% (Forging Brass, C37700 is defined as 100%).

Workability: Capacity for Being Hot Formed (Good), Capacity for Being Cold Worked (Good).

Welding Suitability: Soldering (Good), Brazing (Good), Gas Shielded Arc Welding (Fair), Oxyacetylene Welding (Not Recommended).